



Kooltherm® K10 G2 Soffit Board

INSULATION FOR CONCRETE SOFFITS



- High performance rigid thermoset phenolic insulation
- Fibre-free, closed cell insulation core
- Group 2 for interior lining applications
- Resistant to the passage of water vapour
- Easy to handle and install
- Ideal for new build and refurbishment
- Rodent, mould and fungi resistant
- No CFC or HCFC used in manufacture
- Has zero ODP and low GWP
- NZBC and AS/NZS 4859.1 compliant



Low Energy –
Low Carbon Buildings

Typical Constructions and Total R-values

Concrete Soffit Floor / Roof Installation




Figure 1

| Total R-values for various thicknesses of Kingspan Kooltherm ® K10 G2 Soffit Board | | |
|---|--------------------|--------------------|
| Product Thickness | Heat flow in | Heat flow out |
| Unenclosed sub-floor application (150 mm concrete) | | |
| 25 mm | R _T 1.4 | R _T 1.4 |
| 30 mm | R _T 1.7 | R _T 1.7 |
| 40 mm | R _T 2.1 | R _T 2.1 |
| 50 mm | R _T 2.7 | R _T 2.7 |
| 60 mm | R _T 3.2 | R _T 3.2 |
| 70 mm | R _T 3.7 | R _T 3.7 |
| 80 mm | R _T 4.2 | R _T 4.2 |
| 90 mm | R _T 4.7 | R _T 4.7 |
| Enclosed sub-floor application (150 mm concrete) | | |
| 25 mm | R _T 1.8 | R _T 1.8 |
| 30 mm | R _T 2.1 | R _T 2.1 |
| 40 mm | R _T 2.6 | R _T 2.6 |
| 50 mm | R _T 3.2 | R _T 3.2 |
| 60 mm | R _T 3.8 | R _T 3.8 |
| 70 mm | R _T 4.2 | R _T 4.2 |
| 80 mm | R _T 4.7 | R _T 4.7 |
| 90 mm | R _T 5.2 | R _T 5.2 |

| Total R-values for various thicknesses of Kingspan Kooltherm ® K10 G2 Soffit Board | | |
|---|--------------------|--------------------|
| Product Thickness | Heat flow in | Heat flow out |
| Roof application, no ceiling (150 mm concrete) | | |
| 25 mm | R _T 1.4 | R _T 1.4 |
| 30 mm | R _T 1.7 | R _T 1.7 |
| 40 mm | R _T 2.1 | R _T 2.1 |
| 50 mm | R _T 2.7 | R _T 2.7 |
| 60 mm | R _T 3.2 | R _T 3.2 |
| 70 mm | R _T 3.7 | R _T 3.7 |
| 80 mm | R _T 4.2 | R _T 4.2 |
| 90 mm | R _T 4.7 | R _T 4.7 |
| Roof application, suspended ceiling (150 mm concrete) | | |
| 25 mm | R _T 2.3 | R _T 1.9 |
| 30 mm | R _T 2.6 | R _T 2.1 |
| 40 mm | R _T 3.1 | R _T 2.6 |
| 50 mm | R _T 3.6 | R _T 3.2 |
| 60 mm | R _T 4.2 | R _T 3.7 |
| 70 mm | R _T 4.7 | R _T 4.2 |
| 80 mm | R _T 5.2 | R _T 4.7 |
| 90 mm | R _T 5.6 | R _T 5.2 |

The R-values shown are Total R-values for the building element and are calculated in accordance with AS/NZS 4859.1 and NZS 4214. Kingspan **Kooltherm**® products are manufactured, tested and packaged in conformance with AS/NZS 4859.1.

The contribution of the product Total R-values depends on installation and environmental conditions.

The R-value will be reduced in the event of the accumulation of dust on the upward facing surfaces and in those cavities that are ventilated.

Product Details

Product Description

Kingspan Kooltherm[®] K10 G2 Soffit Board is a super high performance, fibre-free rigid thermoset phenolic insulation core, sandwiched between an upper tissue-based facing and a lower facing of highly reflective aluminium foil autohesively bonded to the insulation core during manufacture.



Kingspan Kooltherm[®] K10 G2 Soffit Board is manufactured without the use of CFCs/HCFCs and has zero Ozone Depletion Potential (ODP) and low Global Warming Potential (GWP).



| Product Data | |
|--------------------------------|---|
| Thermal Conductivity (λ-value) | 0.020 W/mK (Insulant Thickness ≥ 45 mm) 0.021 W/mK (Insulant Thickness 25 - 44 mm) |
| Emittance (Foil Face) | E0.14 |
| Product Dimensions | 2270 mm x 1200 mm (2.72 m ²) |
| Product Thickness | 25, 30, 40, 50, 60, 70, 80, 90 mm |

Product R-value

| Product Thickness | Product R-value |
|-------------------|-----------------|
| 25 mm | R1.2 |
| 30 mm | R1.4 |
| 40 mm | R1.9 |
| 50 mm | R2.5 |
| 60 mm | R3.0 |
| 70 mm | R3.5 |
| 80 mm | R4.0 |
| 90 mm | R4.5 |




Figure 2 Super high performance *Kingspan Kooltherm*[®] K10 G2 Soffit Board

Specification Guide

Kingspan Kooltherm[®] K10 G2 Soffit Board

The soffit insulation shall be *Kingspan Kooltherm*[®] K10 G2 Soffit Board ____ mm thick, with a tested smoke obscuration of not more than 100 m²/kg, comprising a CFC/HCFC-free and zero Ozone Depletion Potential (ODP) rigid thermoset phenolic insulation core with a tissue based facing on one side and composite foil on the other side, manufactured under a management system certified to ISO 9001:2015, ISO 14001:2015, OHSAS 18001:2007 and ISO 50001:2011 by Kingspan Insulation Limited and shall be installed in accordance with the instructions issued by them.

A Project Specific Warranty provided by Kingspan Insulation must be submitted.

Standards and Approvals

Kingspan Kooltherm[®] K10 G2 Soffit Board is manufactured to the highest standards and certified under the following management systems:

| Standard | Management System |
|------------------|------------------------------|
| ISO 9001:2015 | Quality Management |
| ISO 14001:2015 | Environmental Management |
| OHSAS 18001:2007 | Health and Safety Management |
| ISO 50001:2011 | Energy Management |

Product Testing

| Characteristic | Standard | Result |
|-------------------------|---------------------------------------|--|
| Compressive Stress | AS 2498.3 | Typically exceeds 100 kPa at 10% compression |
| Water Vapour Resistance | BS EN 12086:1997 / I.S. EN 12086:1998 | > 100 MN-s/g |

Fire Performance

| Test | Test Method | Result |
|---|-------------|--|
| Ignitability, Flame spread, Heat release, Smoke release | AS 1530.3 | Spread of Flame Index: 0 Smoke Development ≤ 3 |
| Flame Propagation (AS 1366) | AS 2122.1 | Complies |
| NZBC Group Number in accordance with Clause C3.4 | ISO 9705 | Group 2-S Av. Smoke Production Rate no greater than 5.0 m ² s ⁻¹ (0-10 min) |

Durability

If correctly applied, *Kingspan Kooltherm*[®] products can be expected to have a long life of service.

Their durability depends on the supporting structure and the conditions of its use.

Kingspan Kooltherm[®] products are warranted for a period of 10 years for both residential and commercial installations.*

** Subject to the terms of the complete Kingspan Kooltherm[®] warranty document which is available upon request or downloadable from www.kingspaninsulation.co.nz*

Environmental Data

| Aspect | Characteristic |
|---|---|
| Recyclability | Non-contaminated insulation site waste is recyclable, but there are currently no facilities in Australia to process returned material |
| Re-usability | Re-usable if removed with care (long term of service expected) |
| Water Use | No water used in Kingspan Insulation's manufacturing process |
| Blowing Agent Global Warming Potential (GWP) | Manufactured with a blowing agent that has low GWP |
| Blowing Agent Ozone Depletion Potential (ODP) | Manufactured with a CFC/HCFC-free blowing agent that has zero ODP |
| Packaging | Contains 0% recycled product Polythene wrap and EPS skids 100% recyclable |

Installation Instructions

Fixing Directly to Concrete Soffits

Kingspan Kooltherm® K10 G2 Soffit Board can be fully restrained to a concrete soffit by the use of minimum 11 No. appropriate insulation fasteners with a minimum head diameter of 35 mm.

1. The fasteners should be evenly distributed over the whole area of the board and must offer a minimum 40 mm penetration into a solid substrate. Alternatively, a designer can calculate the required design strength to identify a suitable embedment for the design loading.
2. Board joints can be either staggered (see Figure 5) or squared (see Figure 6) and taped with 96 mm wide silver *Kingspan Insulation Tape*. 4 No. fasteners along each length - no less than 50 mm - no more than 150 mm from edge of board, 3 No. fasteners along the middle (offset from edge positions as per diagram Figure 3).
3. Where the board may be subject to external wind pressure, the requirement for additional fixings should be assessed in accordance with appropriate wind load standards.
4. Consideration should be given to the material the fixing is made from and should be deemed appropriate for application, exposure and fire rating by the fixing manufacturer.




Figure 3 Fastener pattern (11 No. per board)
Board size to 2.270 x 1.200 - 4.03 fixings / m²

Why 11 fixings?

Best practice determines that any rigid board insulation, not just *Kingspan Kooltherm*® K10 G2 Soffit Board, should be fixed with 11 mechanical fixings for very good reasons:

- There will always be differential expansion and contraction between any rigid insulation material and adjacent building products due to varying moisture content and temperature.
- In any concrete forming, there will be an uneven surface throughout the slab.
- Where concrete formwork is joined it is normal to have ridges of up to 3 mm which make the concrete surface uneven.
- An insulation board held horizontally may bow like any other sheetmaterial under its own weight.

Using 11 fixings ensures that the insulation board has a strong and permanent fix under the concrete soffit and that it is not compromised by any of the above issues. It also provides a proven robust fire safe solution.

These best practice recommendations are a result of over 30 years of Kingspan Insulation experience in soffit applications.




Figure 4 Side elevation - Concrete Soffit with *Kingspan Kooltherm*® K10 G2 Soffit Board




Figure 5 Board joints staggered




Figure 6 Board joints squared



Installation Instructions (continued)

Fixing to Timber Battens / Furring Channels

1. Alternatively, a treated softwood batten/furring channel lay-out may be adopted if there is an uneven surface or mechanical services present and direct fixing is not possible.
2. 50 mm x 25 mm battens/furring channels should be placed at 600 mm centres to coincide with the edges/centres of the boards.
3. The battens/furring channels should be fixed to the soffit by the use of a suitable fixing method e.g. shot-fire may be considered.
4. *Kingspan Kooltherm*® K10 G2 Soffit Board should then be fixed to the treated timber battens/furring channels using suitable fixings. These should be placed at maximum 300 mm (maximum 200 mm when using nails into timber) in rows not greater than 600 mm apart.
5. Where the board may be subject to external wind pressure, the requirement for additional fixings may need to be assessed in accordance with appropriate wind load standards.

For advice on ancillary materials, such as fixings and tapes please contact our Technical Services Department.



Installation around Fire Collars

1. Fitting *Kingspan Kooltherm*® K10 G2 Soffit Board tight to the fire collar is recommended to reduce the effects of thermal bridging through the slab.
2. Do not cover the face of the fire collar. For fire collars to activate in a fire situation the front face needs to be exposed. This is particularly important when using cast-in collars as the face will be flush with the concrete and it would be easy to cover with the insulation board.



Figure 7 Penetration example - *Kingspan Kooltherm*® K10 G2 Soffit Board installed tight around the fire collar and HDPE service pipe.



Scan to see installation video
"Fixing Directly to Concrete Soffits"

General

Cutting

Cutting should be carried out either by using a fine toothed saw, or by scoring with a sharp knife, snapping the board over a straight edge and then cutting the facing on the other side. Ensure accurate trimming to achieve close-butting joints and continuity of insulation.

Taping

For all fixing methods board joints should be taped with 96 mm wide silver *Kingspan Insulation Tape*.

1. Firstly, ensure that the climate conditions are suitable for the tape being used as well as the product the tape is to be applied too.
2. The surface of the *Kingspan Kooltherm*[®] to which aluminium foil tape is being applied, should be free of dust, dirt or oils. In any case, the surface should be cleaned with a dry cloth before application of the tape.
3. The release liner on the tape should be removed 300 - 600 mm at a time and the adhesive face pressed firmly onto the insulation facing. Care should be taken not to stretch the tape tightly as this will create buckles and voids in the contact area.
4. Care must also be taken to apply the tape over the centre of the joint so that there is adequate area on both sides of the joint for the tape to bond. Uneven width distribution also puts additional shear stress on the smaller side of the butt joint.
5. The tape should then be wiped firmly from the centre out (like wallpaper) with a plastic squeegee. The more pressure that is applied, the more surface contact will be reached, therefore, the greater the bond surface.
6. The tape should then be cut and fitted with a knife and scissors. The same wiping instructions should then be used as above.

In the absence of other protection exposed board edges should be protected by 96 mm wide silver *Kingspan Insulation Tape* with a minimum 48 mm wide overlap onto the board face (see Figure 8) or alternatively use a UPVC c-section.




Figure 8

Packaging

According to quantity, the boards are supplied in packs, labelled and shrink-wrapped in polythene.

Handling and Storage

Storage

The packaging of *Kingspan Kooltherm*[®] should not be considered adequate for long term outdoor protection. Ideally boards should be stored inside a building. If, however, outdoor storage cannot be avoided then the boards should be stacked clear of the ground and covered with an opaque polythene sheet or weatherproof tarpaulin. Boards that have been allowed to get wet should not be used.

Resistance to Solvents

The insulation core is resistant to short-term contact with petrol and with most dilute acids, alkalis and mineral oils. However, it is recommended that any spills be cleaned off fully before the boards are installed. Ensure that safe methods of cleaning are used, as recommended by suppliers of the spilt liquid. The insulation core is not resistant to some solvent-based adhesive systems, particularly those containing methyl ethyl ketone. Adhesives containing such solvents should not be used in association with this product. Damaged boards or boards that have been in contact with harsh solvents or acids should not be used.

OH & S

Kingspan Insulation products are chemically inert and safe to use. A Product Safety Information sheet is available from Kingspan Insulation Pty Ltd.

Please note that the reflective surfaces on this product are designed to enhance their thermal performance. As such, they will reflect light as well as heat, including ultraviolet light. Therefore, if these boards are being installed during bright or sunny weather, it is advisable to wear UV protective sunglasses or goggles and if the skin is exposed for a significant period of time, to protect bare skin with a UV block sun cream.

Foil facings are conductive to electricity - avoid contact with un-insulated electrical cables and fittings.

Contact Details

General Enquiries

Tel: 0800 1 23 23 1

Email: info@kingspaninsulation.co.nz



Kingspan Insulation Pty. Ltd. reserves the right to amend product specifications without prior notice. The information, technical details and fixing instructions etc. included in this literature are given in good faith and apply to uses described. Recommendations for use should be verified as to the suitability and compliance with actual requirements, specifications and any applicable laws and regulations. For other applications or conditions of use, Kingspan Insulation offers a Technical Advisory Service the advice of which should be sought for uses of Kingspan Insulation products that are not specifically described herein. Please check that your copy of the literature is current by contacting us or visiting www.kingspaninsulation.co.nz



Kingspan Insulation Pty Ltd

Tel: 0800 1 23 23 1

Email: info@kingspaninsulation.co.nz

www.kingspaninsulation.co.nz